



GARDICO INCORPORATED

4912 - 14th Avenue NW Seattle, WA 98107-5111

Styles of Industrial Felt

Typical uses: gaskets, cushioning and lubricating

SAE Standard	Trade Designation	Color	Nominal Wool Content %	Actual wool, min %	Roll width, inches	Thickness, inches
F-1	Backcheck	White	100	95	60	1/8 - 1
F-3	Backcheck	Gray	95-100	85	60	1/8 - 1
F-5	Extra firm pad	White	100	95	60	1/8 - 1
F-7	Extra firm pad	Gray	85-95	80	72	1/8 - 1
F-10	Firm pad	White	100	95	72	1/8 - 1
F-11	Firm pad	Gray	95-100	87	72	1/8 - 1
F-13	Firm pad	Gray	80-85	75	72	1/8 - 1
F-15	Firm pad	Gray	60-65	55	72	1/8 - 1
F-26	Soft pad	Gray	50-55	45	72	1/8 - 1
F-50	Ball Bearing	White	100	98	60	1/16 - 3/32
F-51	Ball Bearing	Gray	100	92	72	1/16 - 3/32
F-55	Lining	Gray or Blk	80-85	75	72	1/16 - 3/32